


CATALOG NUMBER	"L"	"T"	"D"	"C"	THREAD
PS29956CW	6.0	4.0	.63	.25	5/8-11UNC-2A
PS29957CW	7.0	4.0	.63	.25	5/8-11UNC-2A
PS29958CW	8.0	4.0	.63	.25	5/8-11UNC-2A
PS29959CW	9.0	4.0	.63	.25	5/8-11UNC-2A
PS29960CW	10.0	6.0	.63	.25	5/8-11UNC-2A
PS29962CW	12.0	6.0	.63	.25	5/8-11UNC-2A
PS29964CW	14.0	6.0	.63	.25	5/8-11UNC-2A
PS29966CW	16.0	6.0	.63	.25	5/8-11UNC-2A
PS29968CW	18.0	6.0	.63	.25	5/8-11UNC-2A
PS29970CW	20.0	6.0	.63	.25	5/8-11UNC-2A
PS29982CW	12.0	6.0	.75	.38	3/4-10UNC-2A
PS29984CW	14.0	6.0	.75	.38	3/4-10UNC-2A
PS29986CW	16.0	6.0	.75	.38	3/4-10UNC-2A
PS29988CW	18.0	6.0	.75	.38	3/4-10UNC-2A
PS29990CW	20.0	6.0	.75	.38	3/4-10UNC-2A
PS29992CW	22.0	6.0	.75	.38	3/4-10UNC-2A
PS29994CW	24.0	6.0	.75	.38	3/4-10UNC-2A
PS2050465CW	26.0	6.0	.75	.38	3/4-10UNC-2A

-NOTES-

- BOLT MATERIAL: STEEL CONFORMING TO THE FOLLOWING PROPERTIES:
 - AVERAGE MIN. ABSORPTION OF 20J WHEN TESTED AT -20°C PER ASTM A370.
 - MINIMUM BOLT BREAKING STRENGTH WHEN TESTED PER ASTM F606:
 - 14100 LBS (62.8 kN) FOR 5/8" BOLTS
 - 22000 LBS (98 kN) FOR 3/4" BOLTS
 - THE EYEBOLT SHALL BE CAPABLE OF BEING BENT (COLD) THROUGH AN ANGLE OF 45° AT THE JUNCTION OF THE EYE AND THE BOLT.
- HOT DIP GALV. AFTER FABRICATION PER CSA G164-M (LATEST REV.).
- NUT DIMENSIONS PER ASME/ANSI B18.2.2. NUT MATERIAL SAME AS BOLT MATERIAL. TAP NUT AFTER GALVANIZING.

CHANCE®		 HUBBELL® POWER SYSTEMS POWER SYSTEMS, INC.	
TITLE 5/8" & 3/4" OVALEYE BOLT (COLD WEATHER)			
CONFIDENTIAL: THIS DRAWING AND ITS CONTENTS ARE CONFIDENTIAL AND THE EXCLUSIVE PROPERTY OF HUBBELL POWER SYSTEMS. NO PUBLICATION, DISTRIBUTION OR COPIES MAY BE MADE WITHOUT THE WRITTEN CONSENT OF HUBBELL POWER SYSTEMS. HUBBELL POWER SYSTEMS UNPUBLISHED. ALL RIGHTS RESERVED UNDER THE COPYRIGHT LAWS.	SIZE	DWG NO.	CAT / PART / ASSY NO.
	C	SAPS29956CW	SEE CHART
DO NOT SCALE THIS DRAWING	DRN BY	DATE	SHEET
	H0EK	9/18/19	01 OF 01